

(19) World Intellectual Property
Organization
International Bureau




(43) International Publication Date
6 May 2004 (06.05.2004)

PCT

(10) International Publication Number
WO 2004/038702 A1

- (51) International Patent Classification⁷: **G11B 5/64**, C23C 14/02, 28/00
- (74) Agents: **OKABE, Masao** et al.; No. 602, Fuji Bldg., 2-3, Marunouchi 3-chome, Chiyoda-ku, Tokyo 100-0005 (JP).
- (21) International Application Number: PCT/JP2003/013471
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 22 October 2003 (22.10.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 2002-308367 23 October 2002 (23.10.2002) JP
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant (*for all designated States except US*): **CANON KABUSHIKI KAISHA** [JP/JP]; 3-30-2, Shimomaruko, Ohta-ku, Tokyo 146-8501 (JP).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **YASUI, Nobuhiro** [JP/JP]; c/o CANON KABUSHIKI KAISHA, 3-30-2, Shimomaruko, Ohta-ku, Tokyo 146-8501 (JP). **DEN, Tohru** [JP/JP]; c/o CANON KABUSHIKI KAISHA, 3-30-2, Shimomaruko, Ohta-ku, Tokyo 146-8501 (JP).
- Published:**
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: STRUCTURED MATERIAL, MAGNETIC RECORDING MEDIUM UTILIZING THE SAME, AND MAGNETIC RECORDING/REPRODUCING APPARATUS



(57) Abstract: ABSTRACT The invention provides a structured material composed by including a noble metal, in which an oriented layer is formed on a layer containing a Group 4A metal. The invention enables to form an oriented layer, which has required a high temperature for formation, by a low temperature process.

DESCRIPTION

STRUCTURED MATERIAL, MAGNETIC RECORDING MEDIUM
UTILIZING THE SAME, AND MAGNETIC
5 RECORDING/REPRODUCING APPARATUS

TECHNICAL FIELD

The present invention relates to a structured material having an oriented layer, which is more
10 specifically adapted for use for example in a vertical magnetic recording medium or the like.

BACKGROUND ART

An oriented film of a noble metal is currently
15 attracting attention, for controlling an orientation of a recording layer in a vertical magnetic recording medium for the next generation, or as an electrode layer or an undercoat layer for controlling an orientation of a ferroelectric oxide in a
20 ferroelectride oxide device. In particular, a (001) oriented layer of Pt, Pd or Ir is considered important.

However, it is already known that a thin film of such noble metals tends to show the (111)
25 orientation in a sputtering method usually executed at the room temperature and in the argon atmosphere, regardless of the substrate material. Consequently

it is difficult to easily obtain a (001) oriented film of a noble metal.

There have been found several ways to obtain a (001) oriented noble metal film. A non-patent
5 reference 1 (Kenji Iijima et al., J. Appl. Phys., 60(1), p.361, 1 July 1986) describes that a Pt (001) oriented film can be obtained on a MgO (001) substrate by elevating the substrate temperature to 600°C and adding oxygen by 50% in an argon gas used
10 as a sputtering gas.

However, the aforementioned technology relating to the oriented film requires to elevate the substrate temperature in the manufacturing process. Therefore the present invention provides a novel
15 oriented film and a production method thereof, not requiring a high temperature of the substrate.

DISCLOSURE OF THE INVENTION

The present invention provides a structured
20 material composed by including a noble metal, comprising an oriented film provided on a layer containing a Group 4A metal.

The present invention also provides a magnetic recording medium including, on a substrate and in
25 order from the substrate side, a MgO (001) layer, a layer containing a Group 4A metal, an oriented layer and a recording layer.

The present invention also provides a method for producing a structured material, comprising a first step of preparing a member having an MgO (001) layer, a second step of forming a layer containing a Group 4A metal on the MgO (001) layer, and a third step of forming an oriented layer composed by including a noble metal on the layer containing the Group 4A metal.

The present invention further provides a magnetic head capable of conducting magnetic recording on a magnetic recording medium including, on a substrate and from the side thereof, a MgO (001) layer, a layer containing a Group 4A metal, an oriented layer and a recording layer, and a magnetic recording/reproducing apparatus provided with a magnetic head drive section for driving such magnetic head.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a schematic view showing an embodiment of a noble metal oriented layer of the present invention;

Fig. 2 is a schematic view showing a magnetic recording medium utilizing a noble metal oriented layer;

Figs. 3A and 3B are schematic view of a recording layer;

Fig. 4 is a conceptual view showing a magnetic recording/reproducing apparatus; and

Fig. 5 is a conceptual view of an information processing apparatus.

5

BEST MODE FOR CARRYING OUT THE INVENTION

(First embodiment: oriented layer)

Now, an oriented layer of the present invention will be explained with reference to Fig. 1. Fig. 1
10 is a schematic view showing the configuration of a structured material of the present invention.

An oriented layer 13 of the invention, composed by including a noble metal, is characterized in that it is provided on a MgO (001) layer 11 through a
15 Group 4A metal containing layer 12. Such oriented layer 13, MgO layer 11 and Group 4A metal containing layer 12 may be collectively called a multi-layered film, a multi-layered functional film or a multi-layered oriented film.

20 Referring to Fig. 1, there are shown a substrate 10, a MgO (001) layer 11, an orientation control layer (layer containing a Group 4A metal) 12, and an oriented layer 13 composed by including a noble metal.

25 The substrate 10 may be arranged under the MgO layer according to the necessity, and may be composed of any material such as glass that can withstand

heating to about 250°C.

The MgO (001) layer 11 may be formed as a bulk member or a thin film. However, in case of a thin film, it is necessary to prepare a film having the
5 (001) orientation for example by sputtering. In case of utilizing a bulk member, it is naturally possible to dispense with the aforementioned substrate.

The orientation control layer (Group 4A metal layer) 12 preferably has a thickness of 0.1 to 3.0 nm,
10 particularly preferably 0.4 to 1.0 nm. Consequently, in case the orientation control layer (Group 4A metal layer) 12 is extremely thin, it may not be a complete film but can also be dispersed in an island shape or shaped as a pattern on the MgO (001) layer 11. Also
15 in the orientation control layer (Group 4A metal layer) 12, it is possible to employ Ti, Zr, Hf or a combination thereof. In particular, Ti is preferred. Also it may be formed in a multi-layered configuration.

20 Also for the noble metal oriented layer 13, it is possible to use Pt, Pd, Ir, Rh, Ag or a combination thereof. In particular, Pt or Pd is effective. A film formation by sputtering on the aforementioned orientation control layer (Group 4A
25 metal layer) 12 provides sufficient (001) orientation in case the temperature of the substrate is 250°C or higher.

Thus, the oriented layer of the present invention is characterized in that it can be sufficiently oriented at a temperature lower than 600°C, for example at a heating temperature range of 300°C or lower. Naturally an oriented state can be obtained also at a higher temperature range.

The degree of orientation of the noble metal oriented layer 13 is indicated by the intensity ratio of X-ray diffractions of Pt (002) and Pt (111). More specifically it is represented by:

$$\text{Orientation degree (\%)} = 100 \times F_{\text{Pt}(002)} / [F_{\text{Pt}(002)} + F_{\text{Pt}(111)}] \quad [1]$$

The degree of orientation of the noble metal oriented layer of the present invention is not particularly restricted as long as such oriented layer can be practically applied to a device utilizing such oriented layer, but it is preferred that the degree of orientation represented by the equation [1] is 99% or higher.

Also the noble metal oriented layer need not be composed singly of Pt, Pd, Ir, Rh or Ag, but may be formed by a mixture such as PtPd or may include other elements such as Ti, Zr, Hf etc. Also there may naturally be adopted a multi-layered configuration containing such noble metal.

(Second embodiment: example of device configuration)

(Configuration of vertical magnetic recording medium utilizing noble metal oriented layer)

In the following an example of a vertical magnetic recording medium utilizing a noble metal oriented layer will be explained with reference to Fig. 2.

A soft magnetic layer, a protective layer and a lubricant layer are preferably applied when necessary, and there will be explained a configuration incorporating all these layers.

Referring to Fig. 2, there are shown a substrate 10, a soft magnetic layer 21, a MgO (001) layer 11, an orientation control layer (Group 4A metal layer) 12, a noble metal oriented film layer 13, a recording layer 22, a protective layer 23, and a lubricant layer 24.

As the substrate 10, there can be employed a flat substrate such as a glass substrate or an aluminum substrate for a hard disk. The soft magnetic layer 21 is required, in a vertical magnetic recording, in order to concentrate a magnetic field from a head to the recording layer 22. The layers 11 to 13 are utilized for attaining orientation of a hard magnetic material formed for example by $L1_0$:CoPt or $L1_0$:FePt of the recording layer 22. The protective layer 23 and the lubricant layer 24 are utilized for improving resistance to the friction and the abrasion

between the head and the medium.

The soft magnetic layer 21 is preferably of a high magnetic permeability such as NiFe or FeCo, but, in consideration of noise generation resulting from magnetic wall displacement, there is preferred a material capable of separating a magnetic member thereby to fix the magnetic wall, such as FeTaC.

Also the recording layer 22 is preferably orientation controlled by the effect of the oriented film including the noble metal. Particularly in a production by an electroplating method, the effect of the oriented film including the noble metal is conspicuous. Also the recording layer 22 is preferably in a state in which a rod-shaped magnetic material of a diameter of 3 to 10 nm is uniformly dispersed in a non-magnetic material. In such situation, the magnetic material is preferably composed of a material of a high vertical magnetic anisotropy such as $L1_0$:CoPt, $L1_0$:FePt etc. However, as the magnetic material, there can also be conceived a multi-layered film of Co/Pt or Co/Pd in addition to $L1_0$:CoPt, $L1_0$:FePt etc., so that the foregoing examples are not restrictive but the high vertical magnetic anisotropy is an important factor. Also the manufacture is not limited to the electroplating method, and there can also be employed a film formation in vacuum such as a sputtering method.

For the protective layer 23, resistance to abrasion is important, and a diamond-like carbon is useful. Also the film thickness is preferably as thin as possible within such an extent as not to deteriorate the effect. Also the lubricant layer 24 is provided to attain smooth displacement between the head and the medium, and can be formed by applying a lubricant coat such as perfluoropolyether.

In the foregoing, there has been explained a vertical magnetic recording medium utilizing the oriented layer of the present invention, but a functional element or a functional device having such oriented layer can be a functional element (so-called ferroelectric memory) provided with a ferroelectric film (for example a ferroelectric film or a film of a high dielectric property having a perovskite structure or a layered structure such as of BT, PT, PZT or SBT) on such oriented layer.

Examples

(Example 1)

The present example employs Ti for the orientation control layer (Group 4A metal layer) and Pt and Pd as the noble metal, and shows an effect by incorporation of a Ti layer.

At first a MgO substrate was introduced in a sputtering apparatus, and the substrate was heated to 300°C. Argon was introduced from a basic pressure of

4.0 × 10⁻⁵ Pa, and after a reverse sputtering for 120 seconds with an RF power of 150 W and a pressure of 7.0 × 10⁻¹ Pa, a Ti film was formed with a thickness of 4.5 Å and an RF power of 150 W. Subsequently a Pt, and Pd layers was formed with a thickness of 20 nm and an RF power of 300 W. On the other hand, there was also prepared a sample bearing a Pt and Pd layers prepared under the same conditions without forming the Ti layer. The Ti layer need not be a complete film, and the described film thickness is a value when converted into a film.

Four samples with combination of presence or absence of the Ti layer and Pt and Pd layers were subjected to X-ray diffraction measurement to calculate the degree of orientation of the Pt and Pd layers.

As a result, as shown in Table 1, either the Pt or Pd layer did not show the (002) diffraction in the absence of the Ti layer, and the degree of orientation represented by the equation [1]:

$$\text{degree of orientation [\%]} = 100 \times F(002) / [F(002) + F(111)]$$

was 0 %. On the other hand, in the presence of the Ti layer, both layers had a high degree of orientation exceeding 99%.

Table 1

	Orientation (%) of Pt layer	Orientation (%) of Pd layer
Ti layer present	0 %	0 %
Ti layer absent	99.4 %	99.1 %

(Example 2)

This examples shows how an orientation of a noble metal, particularly Pt, is possible at low
5 temperatures.

A MgO substrate was introduced in a sputtering apparatus, and the substrate was heated with four temperature conditions of room temperature, 200°C, 250°C and 300°C. At each temperature, as in Example 1,
10 argon was introduced from a back pressure of 4.0×10^{-5} Pa, and, after a reverse sputtering for 120 seconds with an RF power of 150 W and a pressure of 7.0×10^{-1} Pa, a Ti film was formed with a thickness of 4.5 Å and an RF power of 150 W. Subsequently a Pt
15 layer was formed with a thickness of 20 nm and an RF power of 300 W.

An X-ray diffraction measurement was conducted in order to confirm whether these films were oriented.

As a result, as shown in Table 2, the degree of
20 orientation (%) at each temperature was calculated by the equation [1]:

$$\text{degree of orientation [\%]} = 100 \times F(002) / [F(002) + F(111)].$$

Table 2

	room temp.	200°C	250°C	300°C
degree of orientation (%)	0 %	29.1 %	99.3 %	99.4 %

From these results, it was confirmed that the degree of orientation changed significantly between 200°C and 250°C, and that the orientation was 99% or
5 higher at about 250°C or higher. The above-mentioned temperature is a temperature of the substrate, but can be considered substantially equal to the temperature of the Group A4 metal layer.

(Example 3)

10 This example relates to a magnetic recording medium utilizing the aforementioned noble metal oriented film.

At first there was prepared a glass substrate for a hard disk, on which a soft magnetic layer was
15 formed with a thickness of 300 nm and a MgO (001) layer was formed thereon with a thickness of 3 nm. Then a Ti layer of a thickness of 0.45 nm and a Pt layer of a thickness of 5 nm were formed under the sputtering conditions of the substrate temperature of
20 250°C in Example 2, thereby obtaining a noble metal oriented film.

Also a film of a thickness of 25 nm, in which cylinders of $L1_0$:FePt dispersed in silicon oxide as shown in Figs. 3A and 3B, was formed thereon as a

recording layer, and a protective film of diamond-like carbon of a thickness of 3 nm and a lubricant layer of perfluoropolyether were applied. The cylinders of $L1_0$:FePt in the recording layer had a diameter of 5 to 6 nm. The recording layer was formed by a method of electroplating with FePt the silicon oxide film with fine pores of 5 to 6 nm utilizing Pt of the noble metal oriented film as an electrode layer, and then executing thermal treatment to obtain a finely dispersed cylinders of $L1_0$:FePt. In this method, because of the effect of the noble metal oriented film, the cylinders of $L1_0$:FePt were also oriented in the (001) direction.

A similar medium was also prepared utilizing a Pt layer of (111) orientation instead of the noble metal oriented film. In this case, the cylinders of $L1_0$:FePt were oriented in the (111) direction.

There were also prepared samples without the soft magnetic layer, respectively for Pt(001) and Pt(111).

At first, in a comparison of the samples having only the recording layer without the soft magnetic layer, the sample utilizing the noble metal oriented film of Pt (001) showed a high vertical magnetic anisotropy in the direction perpendicular to the substrate, with a squareness ratio of 0.95 in an M-H curve, but the sample utilizing the Pt (111) film

showed a squareness ratio of about 0.5 in the M-H curve, both in the in-plate and in the vertical directions. It was therefore confirmed that the sample employing the noble metal oriented film of Pt (001) was usable as a vertical magnetic recording medium.

Also when the samples having the soft magnetic layer are subjected to recording by bringing it into contact with a magnetic head, vertical magnetic recording can be confirmed in the sample utilizing the noble metal oriented film of Pt (001) and having the vertical magnetic anisotropy by observation with a magnetic force microscope. It can therefore be confirmed that the vertical magnetic recording medium, utilizing the noble metal oriented film of Pt (001) etc. is effective.

However, the formation of the recording layer is not limited to the method explained in the foregoing, but can also be attained for example by sputtering a multi-layered film of Co/Pt or Co/Pd in an oriented state on a noble metal oriented film. It is also possible to form a granular film of $Ll_0:FePt$ or $Ll_0:CoPt$.

(Example 4)

This example provides a magnetic recording apparatus of a configuration as schematically shown in Fig. 4.

In the medium of the present invention, a magnetic material in the recording layer is oriented by the noble metal oriented film, and information can be recorded by the magnetizing direction of a plurality of cylindrical magnetic materials. Therefore, a magnetic recording apparatus can be constructed by incorporating the recording medium of the present invention in an apparatus including a magnetic medium driving section 42, a magnetic head 43, a magnetic head drive section 44 and a signal processing section 45. However, the present example does not limit the drive of the magnetic recording medium to a rotational motion only, nor the drive of the magnetic head to a circumferential sliding motion only.

(Example 5)

The present example relates to an information processing apparatus.

Since the magnetic recording/reproducing apparatus described in Example 4 is capable of information input and output, it is possible to construct an information processing apparatus including, within a casing 51, the aforementioned magnetic recording/reproducing apparatus section 52, a memory section 54, a processing section 53, an external input/output section 56, a power source 55 and connecting wirings 57. Also it is naturally

possible to construct an information processing apparatus by externally (or internally) connecting the aforementioned magnetic recording/reproducing apparatus with a computer including a CPU.

- 5 The present invention allows to provide, in forming a noble metal oriented layer including a noble metal and having a (001) orientation, an oriented layer which can be formed at a low temperature less than 600°C by providing a layer
10 including a Group 4A metal.

CLAIMS

1. A structured material composed by including a noble metal, comprising an oriented layer formed on a layer containing a Group 4A metal.

5

2. The structured material according to claim 1, wherein said layer containing the Group 4A metal is provided on a MgO (001) layer.

10

3. The structured material according to claim 1, wherein said layer containing the Group 4A metal has a thickness within a range of from 0.1 to 3.0 nm.

4. The structured material according to claim 1, wherein said noble metal is Pt, Pd, Ir, Rh, Ag or a combination thereof.

5. The structured material according to claim 1, wherein said layer containing the Group 4A metal is a Ti layer, a Zr layer, a Hf layer or a layer constituted of a combination of these metals.

6. The structured material according to claim 2, wherein said layer containing the Group 4A metal is dispersed in the shape of islands on said MgO (001) layer.

25

7. A magnetic recording medium characterized in including, on a substrate and in order from the substrate side, a MgO (001) layer, a layer containing a Group4A metal, an oriented layer, and a recording
5 layer.

8. A magnetic recording/reproducing apparatus comprising:

a magnetic head capable of a conducting
10 magnetic recording on a magnetic recording medium comprising, on a substrate and in order from the substrate side, a MgO (001) layer, a layer containing a Group 4A metal, an oriented layer, and a recording layer; and

15 a magnetic head driving section for driving said magnetic head.

9. A method for producing a structured material comprising:



20 a first step of preparing a member having a MgO (001) layer;

a second step of forming a layer containing a Group 4A metal on said MgO (001) layer; and



a third step of forming an oriented layer
25 composed by containing a noble metal on said layer containing the Group 4A metal.

10. The method for producing a structured material according to claim 9, wherein said third step is executed with the temperature of said layer containing the Group 4A metal being equal to or
5 higher than 250°C but lower than 600°C.



1/3

FIG. 1*FIG. 2*

2/3

FIG. 3A*FIG. 3B*

3/3

FIG. 4**FIG. 5**

INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP 03/13471

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 G11B5/64 C23C14/02 C23C28/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 G11B C23C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, INSPEC, PAJ, WPI Data, COMPENDEX

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	A.SATO ET AL.: "Co-Cr-Ta Perpendicular magnetic recording media using Pt seed layer" IEEE TRANSACTIONS ON MAGNETICS., vol. 36, no. 5, 1 September 2000 (2000-09-01), pages 2387-2389, XP001019858 IEEE INC. NEW YORK., US ISSN: 0018-9464	1,4,5
Y	page 2387 -page 2388	2,3,6-10
X	US 2002/086186 A1 (LEE) 4 July 2002 (2002-07-04)	1,4,5
Y	page 1, paragraph 4 page 1, paragraph 11 - paragraph 13 page 2, paragraph 24 page 2, paragraph 28 page 3, paragraph 37; figure 2A	2,3,6-9
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

21 January 2004

Date of mailing of the international search report

28/01/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Magrizos, S

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	J.ARIAKE ET AL.: "Pt and Pd intermediate layers for controlling Co-Cr-Nb-Pt layer growth in double layered perpendicular magnetic recording media" JOURNAL OF MAGNETISM AND MAGNETIC MATERIALS, vol. 242-245, April 2002 (2002-04), pages 311-316, XP004358685 ELSEVIER, AMSTERDAM, NL ISSN: 0304-8853 page 312, right-hand column, line 26 - line 40 -----	1,4,5
Y	WO 99 24973 A (CARNEGIE MELLON UNIVERSITY) 20 May 1999 (1999-05-20) page 16, line 30 - line 35 -----	2,7-10
Y	JP 2001 023140 A (HITACHI) 26 January 2001 (2001-01-26) page 3, paragraph 10 page 4, paragraph 18; figure 2 -----	3
Y	EP 1 186 580 A (SUMITOMO) 13 March 2002 (2002-03-13) page 7, line 48 -page 8, line 12; claims 1,3; figure 1 -----	6

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/JP 03/13471

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 2002086186	A1	04-07-2002	KR 2002057371 A	11-07-2002
			CN 1374641 A	16-10-2002
			JP 2002216341 A	02-08-2002
			SG 96673 A1	16-06-2003
WO 9924973	A	20-05-1999	US 6248416 B1	19-06-2001
			CN 1285948 T	28-02-2001
			DE 69812689 D1	30-04-2003
			EP 1308936 A1	07-05-2003
			EP 1310948 A1	14-05-2003
			EP 1315152 A1	28-05-2003
			EP 1310949 A1	14-05-2003
			EP 1031143 A1	30-08-2000
			JP 2001523032 T	20-11-2001
			TW 418388 B	11-01-2001
			WO 9924973 A1	20-05-1999
JP 2001023140	A	26-01-2001	JP 3220116 B2	22-10-2001
			US 2003203189 A1	30-10-2003
			US 6562453 B1	13-05-2003
EP 1186580	A	13-03-2002	JP 2002144111 A	21-05-2002
			CA 2356042 A1	28-02-2002
			CN 1347785 A	08-05-2002
			EP 1186580 A2	13-03-2002
			US 2002048696 A1	25-04-2002